



481



Specifications

Classification	EN 649	Heterogeneous Pvc
Hardness	DIN 53505	94 Shore A - Spread of hardness Shore 3
Indentation	EN 433	0.04 mm
Wear resistance (after 100 Frick-Taber cycles)	EN 660-2	Loss of volume Fv 1.5 mm ³ Loss of mass Fm 2.0 mg Thickness loss DV 0.00054 mm
Light fastness	ISO 105-B02	>7
Resistance to chemicals	EN 423	Black coffee - after 2 hours: 0 (unchanged) Acetone - after 2 hours: 0 (unchanged) 25% caustic soda solution - after 2 hours: 0 (unchanged) 25% citric acid - after 2 hours: 0 (unchanged)
Fire resistance	EN 13501-1	Bfl-s1
Coefficient of friction	EN 13893	DS (> 0.30)
Surface resistance		$5 \times 10^5 < R < 5 \times 10^6$

Dimention

Art. 1152 ESD
Rolls



Thickness: 2.0 mm
Weight: 3.3 kg/sqm
Format:
Rolls 10 x 1,4 m
Greater lengths
available upon request

Art. 1152 ESD
Tiles



Thickness: 2.0 mm
Weight: 3.3 kg/sqm
Format:
Tiles 608 x 608 mm

Art. 2081 ESD
Self-blocking Tiles



Thickness: 4.0 mm
Weight: 6 kg/sqm
Format:
Tiles 500 x 500 mm
Blocktile type self-
blocking tiles

Art. 3008 ESD
Self-blocking Tiles



Thickness: 4.0 mm
Weight: 5.8 kg/sqm
Format:
Tiles 960 x 480 mm
Puzzle cut self-blocking
tiles

As for all vinyl flooring, prolonged contact with tires or other rubber objects can cause indelible brown marks. Further, as adhesive is not used to fix tiles, forklifts and carts are not recommended. Installation should be carried at least at 18°C. This temperature should be maintained for 24 hours before and after installation. Self blocking tiles roughly require 1cm of space between tiles and walls. Beyond 50 sq. meters the use of expansion joints is mandatory.